


# Yb:GGG



## DESCRIPTION

CRYLINK's Yb:GGG crystal product, also known as Ytterbium-doped Gadolinium gallium garnet (Yb:Gd<sub>3</sub>Ga<sub>5</sub>O<sub>12</sub>). It is a kind of laser crystal product with excellent comprehensive performance. It is widely used in high power laser, semiconductor laser, LD pump field. The product has the characteristics of high doping concentration, wide absorption band and low quantum defect. It can be used in ultra-short pulse laser, high power and high efficiency solid laser, ultra-short pulse laser, semiconductor laser products.

## FEATURES

- Low quantum defects
- Wide absorption band
- High doping concentration
- No excitation state absorption

## APPLICATIONS

- Semiconductor lasers
- Thin-film laser oscillator
- Diode pump Yb: GGG laser
- High-power solid-state lasers



# Yb:GGG

## PRODUCT PARAMETERS

Chemical formula	Yb:Gd <sub>3</sub> Ga <sub>5</sub> O <sub>12</sub>
Crystal structure	Cubic, Ia3d
Lattice parameters	12.38 Å
Zero-phonon line (ZPL)	971nm
σ <sub>abs</sub> (ZPL)	6.6×10 <sup>-25</sup> cm <sup>2</sup>
Broadband absorption	930 nm – 950 nm
Peak emission wavelength(EW)	1021nm
σ <sub>em</sub> (EW)	1.9×10 <sup>-24</sup> cm <sup>2</sup>
Δλ <sub>emission</sub> (FWHM at inversion ~10%)	8nm
Quantum defects	0.8
Thermal conductivity, κ (5 at.%)	7.8 W/m/K
κ (15 at.%)	7.7 W/m/K
Coefficient of thermal expansion	8×10 <sup>-6</sup> ·K <sup>-1</sup>
dn/dT	21.2×10 <sup>-6</sup> K <sup>-1</sup>
αT	8.5×10 <sup>-6</sup> K <sup>-1</sup>
Mohs hardness	7.5
Melting point	1750°C

## SPECTROGRAM

